



Formulation Recommendation White, Zinc-Free, Primer Sealer Based on ALBERDINGK AC 2522

01/08/00

| No./Nr. | Material/Rohstoffe | Supplier/Hersteller | Quantity/Menge |
|--------------------------------------|--------------------|---------------------|----------------|
| 1. | Disperbyk 191 | Byk Chemie | 5.90 |
| 2. | Deionized water | | 12.80 |
| 3. | Foamaster 714 | Cognis | 0.50 |
| 4. | Talkum 20 MO | Finntalc | 7.50 |
| 5. | HALOX® BW-100 | HALOX/CH Erbslöh | 12.80 |
| 6. | Kronos 2310 | Kronos Titan | 10.20 |
| <i>Add no. 1-6 and disperse well</i> | | | |
| 7. | ALBERDINGK AC 2522 | ALBERDINGK BOLEY | 49.60 |
| 8. | Dowanol DPnB* | Dow Chemie | 2.00 |
| 9. | Deionized water* | | 1.00 |
| 10. | Byk 346 | Byk Chemie | 0.30 |
| 11. | Drew T-4202 | Drew Ashland | 0.70 |
| 12. | Nopco DSX 1514 | Cognis | 1.20 |
| | Totals | | 104.50 |

* = premixing (vormischen)

Visit the ALBERDINGK website at www.alberdingk.com