



ALBERDINGK BOLEY
GMBH

ABT. DISPERSIONEN

Tannin barrier varnish

based on : ALBERDINGK AC 2522

	<u>Raw materials</u>	<u>Amount:</u>
1.	ALBERDINGK AC 2522	92,60
2.	Foamex 810	0,50
3.	Drew T-4202	0,70
4.	BYK 346	0,40
5.	Dowanol DPM *	2,50
6.	Dowanol DPnP *premix	2,50
7.	Water *	3,00
8.	Luba Print 460	1,50
9.	Halox XTain L-44	0,50
10.	DSX-3000	0,55