



## Formulation

### Interior 100% Acrylic APEO-Free Glossy Varnish Based LOPON® PO, LOPON® E 100

Raw Materials	Parts per Weight	Class	Supplier
Water	8.00		
LOPON® PO	1.00	Dispersant	ICL
Kronos® 2310	21.50	Titanium Dioxide	Kronos
Ammonia (25%)	0.30	pH adjuster	
Diethylene glycol n-butyl ether acetate	2.20	Solvent	
Texanol	2.50	Coalescent aid	Eastman
Water	6.03		
Mowilith® LDM 7774	58.00	Acrylic emulsion	Celanese
LOPON® E 100	0.30	Defoamer	ICL
Borchi® Gel L 75 N	0.17	Non-ionic thickener	Borchers
<b>TOTAL</b>	<b>100</b>		
Formula Constants		Formula Properties	
% Solids/Wt.	N/A	Density lbs./gal.	N/A
% Solids/Vol.	N/A	KU Visc. @ R.T.	N/A
VOC g/l	N/A		

Disclaimer: Information made available herein is provided for general informational purposes only and not guaranteed to be complete, up-to-date, or accurate in all respects. You should not rely on any information contained herein in making any decision, taking any action or refraining from taking any action. This information is not intended to be a substitute for any technical, regulatory, legal or other professional advice, in the relevant jurisdiction, on any subject matter. All information is made "as is" with no guarantee as to its accuracy or completeness, and without any claim, representation or warranty of any kind (express or implied), including without limitation, any warranties of suitability, reliability, applicability, merchantability, fitness, noninfringement, result, outcome or any other matter. We expressly disclaim all liability in respect to actions taken or not taken based on any of the contents herein. © 2021 ICL Specialty Products Inc. All rights reserved. All information is protected under international copyright conventions.