



Formulation

HALOX 630 in a Clear Acrylic Lacquer for Brass

COMPONENT A :

		<u>% Wt/Wt.</u>	
MEK		6.36	Solvent
Acetone		9.89	Solvent
MIBK		1.73	Solvent
<i>Stir vigorously while adding</i>			
CAB-381-0.5	[1]	7.71	Flow Agent
<i>Mix until clear and homogenous</i>			
Paraloid B-66	[2]	27.71	Acrylic Resin
Santicizer 160	[3]	3.85	Plasticizer
FC-430 Fluorad	[4]	0.03	Surfactant
HALOX 630		1.14	Liq. Organ. Corr. Inh.
MIBK		18.71	Solvent
MEK		18.71	Solvent
Eastman PM Acetate	[1]	4.16	Solvent
TOTAL		<hr/> 100.00	

FORMULA CONSTANTS

% Solids/Wt.	36.25
% Solids/Vol.	38.92
VOC g/L	504.44

FORMULA PROPERTIES

Density	791.27 g/L
---------	------------

SUPPLIER KEY

[1]	Eastman Chemie Company
[2]	Rohm and Haas Deutschland GmbH
[3]	Ferro Corporation
[4]	3M

The information contained herein is correct to the best of our knowledge, but is intended only as a source of information. The recommendations or suggestions herein are made without guarantee of representation as to results, and we suggest that you evaluate the recommendations contained in this formulation in your own laboratory prior to use. Data and results supplied in-part by Ciba Specialty Chemicals and based on controlled or laboratory work.

ParaloidB66/630E

061305