



Formulation

Powder Coating Polyester TGIC HALOX[®] 650

Grind	% Wt./Wt.	Class	Supplier
Crylcoat 2430-0	65.32	Resin	Allnex
Additol P 891	6.54	Flow additive	Allnex
Araldite PT 810	5.41	Crosslinker (TGIC)	Huntsman
Benzoin	0.16	Degassing agent	Estron Chemical
Kronos 2160	9.03	Pigment	Kronos
HALOX [®] 650	2.19	Corrosion inhibitor	ICL
Shieldex C303	11.35	Corrosion inhibitor	Grace Davison
TOTAL	100		

Formula Constants		Formula Properties	
% Solids/Wt.	N/A	Density lbs./gal.	N/A
% Solids/Vol.	N/A	KU Visc. @ R.T.	N/A
VOC g/l	N/A		

Disclaimer: Information made available herein is provided for general informational purposes only and not guaranteed to be complete, up-to-date, or accurate in all respects. You should not rely on any information contained herein in making any decision, taking any action or refraining from taking any action. This information is not intended to be a substitute for any technical, regulatory, legal or other professional advice, in the relevant jurisdiction, on any subject matter. All information is made "as is" with no guarantee as to its accuracy or completeness, and without any claim, representation or warranty of any kind (express or implied), including without limitation, any warranties of suitability, reliability, applicability, merchantability, fitness, noninfringement, result, outcome or any other matter. We expressly disclaim all liability in respect to actions taken or not taken based on any of the contents herein. © 2021 ICL Specialty Products Inc. All rights reserved. All information is protected under international copyright conventions.