



Advanced Additives



FORMULATION

HALOX® CW-314 in an Elastomeric Roof Coating

<u>GRIND</u>	<u>Control</u>		<u>15% HALOX® CW-314</u> Replacement of Calcium Carbonate		<u>10% HALOX® CW-314</u> Replacement of Calcium Carbonate & TiO ₂	
	<u>lbs/100 gal</u>	<u>% wt</u>	<u>lbs/100 gal</u>	<u>% wt</u>	<u>lbs/100 gal</u>	<u>% wt</u>
Water	130.0	11.69	163.5	14.57	180.0	16.13
Tamol 851	4.0	0.36	10.0	0.89	8.0	0.72
Propylene Glycol	6.0	0.54	6.0	0.53	6.0	0.54
DEE FO 1015	1.0	0.09	1.0	0.09	1.0	0.09
KTPP	1.0	0.09	1.0	0.09	1.0	0.09
Zoco 101	30.0	2.70	30.0	2.67	30.0	2.69
Ti-Pure R-960	50.0	4.50	50.0	4.46	40.0	3.58
HALOX® CW-314	0.0	0.00	168.0	14.98	117.0	10.49
HUBERCARB G3	270.0	24.29	109.7	9.78	164.5	14.74
Water	20.0	1.80	20.0	1.78	20.0	1.79
 <u>LETDOWN</u>						
Rhoplex EC- 2885	504.0	45.34	504.0	44.93	504.0	45.17
Texanol	6.5	0.58	6.5	0.58	6.5	0.58
Add grind portion under agitation and mix until uniform.						
DEE FO 1015	6.0	0.54	6.0	0.53	6.0	0.54
Premix the following, then add to above under agitation.						
Water	75.2	6.76	40.0	3.57	25.9	2.32
Natrosol 250 H4BR PA	5.0	0.45	3.0	0.27	3.0	0.27
Mix well for 10 minutes.						
Ammonia Hydroxide (28%)	3.0	0.27	3.0	0.27	3.0	0.27
TOTAL	1111.70	100.00	1121.73	100.00	1115.87	100.00

Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, ICL Advanced Additives ("ICL") makes no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will ICL be responsible for damages of any nature whatsoever resulting from the use or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent, and ICL makes no representation or warranty, express or implied, that the use thereof will not infringe any patent.

NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

© 2018 ICL Advanced Additives, a division of ICL Specialty Products Inc. All rights reserved.

1326 Summer Street, Hammond, Indiana, 46320 USA

P: 219.933.1560 E: techservice@halox.com

www.halox.com

10/18/2018

1 of 2

HALOX[®] CW-314 in an Elastomeric Roof Coating

Description	<u>Control</u>	<u>15% HALOX CW-314</u>	<u>10% HALOX CW-314</u>
% Solids/wt	56.8	57.1	56.9
PVC	34.4	34.4	34.4
VOC g/l	22	22	22
Density lbs/gal	11.12	11.22	11.16
<i>Initial</i>			
Solar Reflectance (ASTM C1549)	0.826	0.848	0.829
Thermal Emittance (ASTM C1371)	0.89	0.90	0.91
<i>After ASTM G155 accelerated weathering (1,000h)</i>			
Solar Reflectance (ASTM C1549)	0.820	0.844	0.827
Thermal Emittance (ASTM C1371)	0.90	0.92	0.92
<i>after ASTM D7897 "soiling"</i>			
Solar Reflectance (ASTM C1549)	0.792	0.823	0.792
Thermal Emittance (ASTM C1371)	0.90	0.90	0.90
<i>Low temperature flexibility ASTM D6083/D522</i>			
Initial	Pass	Pass	Pass
After ASTM G155 accelerated weathering (1,000h)	Pass	Pass	Pass

Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, ICL Advanced Additives ("ICL") makes no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will ICL be responsible for damages of any nature whatsoever resulting from the use or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent, and ICL makes no representation or warranty, express or implied, that the use thereof will not infringe any patent.

NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

© 2018 ICL Advanced Additives, a division of ICL Specialty Products Inc. All rights reserved.

1326 Summer Street, Hammond, Indiana, 46320 USA

P: 219.933.1560 E: techservice@halox.com

www.halox.com

10/18/2018

2 of 2