



# Formulation

## 2K Waterborne Epoxy Dispersion Industrial Maintenance Primer using HALOX SW-111

		LBS	GALS	
<b>COMPONENT A:</b>				<b><u>Formula Constants</u></b>
GRIND				Density (lb/gal) 11.62
EPI-REZ 6520-WH-53	[1]	293.78	32.29	Density (g/L) 1392.41
Dowanol DPnB	[2]	32.11	4.23	Weight Pigment (%) 33.97
EFKA 2526 Defoamer	[3]	3.21	0.42	Volume Pigment (%) 14.17
Disperbyk-190	[4]	5.02	0.57	Weight Solids (%) 63.18
RO-4097 Kroma Red	[5]	71.44	1.75	Volume Solids (%) 48.29
HALOX SW-111	[6]	99.73	4.16	PVC (%) 29.79
Wollastocoat 10ES	[7]	106.66	4.41	VOC (lb/gal) 0.90
Nytal 400	[8]	45.45	1.91	VOC (g/L) 108.26
Sparmite Barytes	[5]	71.44	1.95	
<i>High speed disperse to 4.5 - 5.5 NS Hegman grind, then add the following:</i>				<b><u>Formula Properties</u></b>
EPI-REZ 6520-WH-53	[1]	153.11	16.83	
De-Ionized Water		77.26	9.26	
<b>COMPONENT B:</b>				<b><u>Supplier Key</u></b>
DPC 6870 Curing Agent	[9]	179.60	19.56	[1] Momentive
<i>Premix the next 2 ingredients before adding.</i>				[2] The Dow Chemical Company
HALOX FLASH-X 330	[6]	11.54	1.16	[3] EFKA Chemicals
Dowanol PM Glycol Ether	[2]	11.54	1.50	[4] Byk - Chemie USA Inc.
TOTAL		1,161.89	100.00	[5] Elementis Pigments Inc.
				[6] HALOX
				[7] Nyco Minerals, Inc.
				[8] R.T. Vanderbilt Company, Inc.
				[9] HEXION

The information contained herein is correct to the best of our knowledge, but is intended only as a source of information. The recommendations or suggestions herein are made without guarantee of representation as to results, and we suggest that you evaluate the recommendations contained in this formulation in your own laboratory prior to use.