



Formulation

Temporary Rust Preventative Coating

HALOX[®] 520

Premix these 3 ingredients in the order shown:

Grind	% Wt./Wt.	Class	Supplier
Water	16.4		
Monoethanolamine, Low Freeze Grade	55.88	Solvent	Dow
HALOX [®] 520	27.72	Corrosion inhibitor	ICL
TOTAL	100		
Dilute the above 5, 10 or 20% in de-ionized water and use as a temporary coating			

Formula Constants		Formula Properties	
% Solids/Wt.	N/A	Density lbs./gal.	N/A
% Solids/Vol.	N/A	KU Visc. @ R.T.	N/A
VOC g/l	N/A		

Disclaimer: Information made available herein is provided for general informational purposes only and not guaranteed to be complete, up-to-date, or accurate in all respects. You should not rely on any information contained herein in making any decision, taking any action or refraining from taking any action. This information is not intended to be a substitute for any technical, regulatory, legal or other professional advice, in the relevant jurisdiction, on any subject matter. All information is made "as is" with no guarantee as to its accuracy or completeness, and without any claim, representation or warranty of any kind (express or implied), including without limitation, any warranties of suitability, reliability, applicability, merchantability, fitness, noninfringement, result, outcome or any other matter. We expressly disclaim all liability in respect to actions taken or not taken based on any of the contents herein. © 2021 ICL Specialty Products Inc. All rights reserved. All information is protected under international copyright conventions.