

2K POLYAMIDE CURED EPOXY PRIMER

Salt Spray - CRS - 3 mils / 2 mils TC - % t.f.w.

PRIMER ONLY - 672 hours



PRIMER & TOPCOAT - 1300 hours



BLANK (no inhibitor)

Zinc Chromate @ 4.4%

HALOX 491@ 6.6%


2K POLYAMIDE CURED EPOXY PRIMER

Prohesion - CRS - 3 mils / 2 mils TC - % t.f.w.

PRIMER ONLY - 1,416 hours



PRIMER & TOPCOAT - 1,416 hours



BLANK (no inhibitor)

Zinc Chromate @ 4.4%

HALOX 491@ 6.6%