

PRODUCT RECOMMENDATION GUIDE

HALOX® Corrosion Inhibitors

WATER-BASED SYSTEMS					
	FILM THICKNESS	REALIZABLE SALT SPRAY HOURS	1st RECOMMENDATION	2nd RECOMMENDATION	TO IMPROVE ADHESION (SYNERGY)
ACRYLIC EMULSION PRIMER	<15 microns	100 hours	HALOX® SZP-391 JM 3-5% & HALOX® 550 1-3%	HALOX® 430 JM 3-5% & HALOX® 550 1-3%	—
	25-50 microns	336 hours	HALOX® SZP-391 3-5%	HALOX® 750 3-5%	HALOX® 570 LS or HALOX® 515 1-3%
	>50 microns	500 hours	HALOX® SZP-391 5%	HALOX® 750 5%	HALOX® 570 LS or HALOX® 515 1-3%
DIRECT-TO-METAL HIGH GLOSS ACRYLIC ENAMEL	<25 microns	100 hours	HALOX® SZP-391 JM 1-3%	HALOX® 430 JM 1-3%	HALOX® 570 LS or HALOX® 515 1-3%
	>25 microns	336-500 hours	HALOX® SZP-391 3-5%	HALOX® 430 3-5%	HALOX® 570 LS or HALOX® 515 1-3%
ALKYD EMULSIONS & DISPERSIONS	<25 microns	100-200 hours	HALOX® SZP-391 JM 3% & HALOX® 570 LS 1-3%	HALOX® 550 WF 1-3%	HALOX® 550 WF or HALOX® 515 1-3%
	25-50 microns	336 hours	HALOX® SZP-391 1-3% & HALOX® 550 WF 1-3%	HALOX® 750 3-5%	HALOX® 570 LS or HALOX® 515 1-3%
2K POLYURETHANE	<25 microns	100-200 hours	HALOX® 430 JM 1-3%	HALOX® SZP-391 JM 5%	HALOX® 570 LS 1-3%
	>25 microns	336-500 hours	HALOX® 430 3-5%	HALOX® SW-111 3-5%	HALOX® 570 LS 1-3%
2K EPOXY	<25 microns	336 hours	HALOX® 430 JM 1-3%	HALOX® SZP-391 JM 1-3%	HALOX® 550 WF 1-3%
	>25 microns	500+ hours	HALOX® SW-111 3-5%	HALOX® 430 3-5%	HALOX® 550 WF 1-3%
1K EPOXY	25+ microns	68-336 hours	HALOX® 750 5% or HALOX® 550 2%	HALOX® SW-111 5%	HALOX® 550 WF 1-3%
EPOXY DISPERSION	<25 microns	336 hours	HALOX® 430 JM 1-3%	HALOX® SZP-391 JM 1-3%	HALOX® 570 LS or HALOX® 515 1-3%
	>25 microns	500+ hours	HALOX® SW-111 5-7%	HALOX® 750 5%	HALOX® 570 LS or HALOX® 515 1-3%
POLYVINYLIDENE CHLORIDE (PVDC)	<25 microns	200 hours	HALOX® SZP-391 JM 1-3%	HALOX® 430 JM 1-3%	HALOX® 550 / 550 WF 1-3%

PRODUCT RECOMMENDATION GUIDE

HALOX® Corrosion Inhibitors

WATER-BASED SYSTEMS					
	FILM THICKNESS	REALIZABLE SALT SPRAY HOURS	1st RECOMMENDATION	2nd RECOMMENDATION	TO IMPROVE ADHESION (SYNERGY)
PVDC (Rust Converter Primer)	<25 microns	48-168 hours	HALOX® 550 WF 3-5%	—	—
CATIONIC ACRYLIC (pH<7)	>50 microns	72-100 hours	HALOX® FLASH-X® 330 4-5% <i>Pre-mix (50:50) with Water</i>	—	HALOX® 550 1-2%
CATIONIC ALKYD	>50 microns	200 hours	HALOX® 550/550 WF 1-3%	—	—
CATIONIC POLYURETHANE DISPERSIONS	<50 microns	>200 hours	HALOX® FLASH-X® 330 4-5% <i>Pre-mix (50:50) with Water</i>	—	HALOX® 550 1-3%
ANIONIC POLYURETHANE DISPERSIONS	>50 microns	<200 hours	HALOX® 430 3-5%	HALOX® 570 LS 1-3%	HALOX® 550 1-3%
1K CATIONIC EPOXY (pH<7)	>50 microns	100-500 hours	HALOX® SZP-391 5%	HALOX® 430 JM 5%	HALOX® 550 / 550 WF 1-3%
HYBRID ACRYLIC ALKYD	>50 microns	<200 hours	HALOX® 515 1-3%	HALOX® 570 LS 1-3%	HALOX® 550 / 550 WF 1-3%
ACRYLIC EPOXY (Topcoat)	>50 microns	500+ hours	HALOX® 570 LS or HALOX® 515	HALOX® 550/550 WF 1-3%	—
SILICONE EMULSION	>50 microns	200 hours	HALOX® SZP-391 6-8%	HALOX® 570 LS 1-3%	HALOX® 550 WF 1-3%
RUST PREVENTATIVE COATING (Temporary)	<5 microns	1-24 hours	HALOX® 550/550 WF	—	SEE TDS
PHENOLIC DISPERSIONS	25-50 microns	<500 hours	HALOX® SZP-391 3-5% or HALOX® 550/550 WF 1-2%	HALOX® 750 3-5%	—

PRODUCT RECOMMENDATION GUIDE

HALOX® Corrosion Inhibitors

SOLVENT-BASED SYSTEMS					
	FILM THICKNESS	REALIZABLE SALT SPRAY HOURS	1st RECOMMENDATION	2nd RECOMMENDATION	TO IMPROVE ADHESION (SYNERGY)
2K EPOXY PRIMER (+ high solids)	25-50 microns	500 hours	HALOX® SW-111 5-7%	HALOX® 700 5-7%	HALOX® 630 1-3% HALOX® 550 WF 1-4%
	>50 microns	1000 hours	HALOX® SW-111 7-10% or HALOX® 550 WF 1-3%	HALOX® 700 5-7%	HALOX® 630 1-3%
EPOXY ESTER	<25 microns	336 hours	HALOX® SZP-391 JM 3-5%	HALOX® 430 JM 3-5%	HALOX® 550 WF or HALOX® 630 1-3%
	>25 microns	500+ hours	HALOX® SZP-391 5-7%	HALOX® 750 5-7%	HALOX® 550 WF or HALOX® 630 1-3%
ALKYD	<25 microns	100-200 hours	HALOX® SZP-391 JM 3-5%	HALOX® CW-291 1-3%	HALOX® 550 WF or HALOX® 630 1-3%
	25-75 microns	336-500 hours	HALOX® SZP-391 JM & HALOX® CW-2230 (2:1 ratio) 3-5%	HALOX® SZP-391 & HALOX® CW-291 (2:1 ratio) 3-5%	HALOX® 550 WF 1-3%
2K POLYURETHANE	<25 microns	200 hours	HALOX® SZP-391 JM 1-3%	HALOX® 430 JM 1-3%	HALOX® 550 WF or HALOX® 630 1-3%
	25-75 microns	500+ hours	HALOX® SZP-391 1-3% & HALOX® 550 WF 1-3%	HALOX® 700 3-5%	HALOX® 550 WF 1-3%
MOISTURE CURE POLYURETHANE	>25 microns	336 hours	HALOX® CW-2230 3-5%	HALOX 430 JM 3-5%	HALOX® 550 WF or HALOX® 630 1-3%
WASH (Etch) PRIMERS	<25 microns	336 hours	HALOX® SZP-391 JM 3-5% & HALOX® 550 WF 1-3%	HALOX® 430 JM 3-5% & HALOX® 550 WF 1-3%	—
COIL COATING POLYESTER	>25 microns	500+ hours	HALOX® 430 JM 5% & HALOX® 650 0.5%	HALOX® SZP-391 JM 5% & HALOX® 650 0.5%	
COIL COATING EPOXY PRIMER	<25 microns	500+ hours	HALOX® 430 JM 5-8% & HALOX® 650 0.5%	HALOX® SZP-391 JM 5% & HALOX® 650 0.5%	—
PHENOLIC ALKYD	25-50 microns	336 hours	HALOX® SZP-391 6% & 550 WF 1%	HALOX® SZP-391 6%	HALOX® 630 1%
ACRYLIC TOPCOAT	25-50 microns	200 hours	HALOX® 550 WF 1-3%	HALOX® 630 1-3%	—

PRODUCT RECOMMENDATION GUIDE

HALOX® Corrosion Inhibitors

OTHER SYSTEMS					
	FILM THICKNESS	REALIZABLE SALT SPRAY HOURS	1st RECOMMENDATION	2nd RECOMMENDATION	TO IMPROVE ADHESION (SYNERGY)
SILOXANE (Epoxy) ACRYLIC	75-175 microns	2000 hours	HALOX® 550 / 550 WF 1-3%	—	—
UV CURE URETHANE OR EPOXY ACRYLATE	25-50 microns	500 hours	HALOX® SZP-391 JM 3-5%	HALOX® 570 0.5-2%	HALOX® 550 WF 1-2%
POWDER COATING POLYESTER/TGIC	>25 microns	500 hours	HALOX® 430 JM 5%	—	HALOX® 650 1-2%
POWDER COATING GMA ACRYLIC	>25 microns	500+ hours	HALOX® 550 WF 1-3%	HALOX® 430 5-7%	—
E-COAT CATHODIC	<25 microns	—	HALOX® 550 / 550 WF 1-3%	—	—
E-COAT ANODIC	<25 microns	—	HALOX® 550 1-3%	—	—
SILICONE (Heat Resistant Coating)	30-50 microns	<200 hours	HALOX® SZP-391 5-7%	—	HALOX® 550 WF 1-2%
ZINC RICH PRIMERS	20-40 microns	—	HALOX® 550/550 WF 2-3%	HALOX® SZP-391 JM 2-6%	—

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, ICL Performance Products LP ("ICL") makes no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will ICL be responsible for damages of any nature whatsoever resulting from the use or reliance upon information or the product to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent, and ICL makes no representation or warranty, express or implied, that the use thereof will not infringe any patent. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESSED OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. © 2017 ICL Performance Products LP. All rights reserved.